

## PRODUCT SPECIFICATION



**Item: Advanced Turf®** (supplied by Boddingtons Ltd., Blackwater Trading Estate • The Causeway • Maldon Essex CM9 4GG • England **Tel: +44 (0) 1621 874200 Fax: +44 (0) 1621 874299** and comprising: **Items A. B. & C.**

**A.** 100mm or 150mm or 200 mm \* thick layer of Boddingtons ATS400/B Rootzone. (\*delete as appropriate)

*A compacted layer of pre-blended rootzone material, being a mixture of sand, soil, recycled organic material and Advanced Turf® mesh elements at an inclusion rate of not less than 5kg/m<sup>3</sup>.*

The rootzone thickness layer above shall be determined from Boddingtons Limited published Design Guidance Notes or using advice from Boddingtons Limited.

The Advanced Turf® mesh elements shall have the following properties:

|                          |   |
|--------------------------|---|
| <b>Polymer</b>           | Polypropylene homopolymer                                     |
| <b>Density</b>           | 0.905 - 0.908g/cm <sup>3</sup>                                |
| <b>Element size</b>      | 100mm x 50mm  |
| <b>Mesh pitch</b>        | 10mm + 2mm - 1mm  |
| <b>Tensile strength</b>  | 3.3kN/m width (both longitudinal and transverse directions)   |
| <b>Junction strength</b> | Not less than 50% of the mesh strand strength                 |
| <b>Flexural recovery</b> | The mesh shall have high flexural recovery, not less than 95% |

**B.** Installation fertiliser - 35g/m<sup>2</sup>

**C.** Sandy soil grown turf consisting of the specified amenity grass species.

This system shall be installed in accordance with guidance notes and advice provided by Boddingtons Limited.

**Note to specifier:** *This specification does not include provision or preparation of materials below the Advanced Turf® Rootzone or the maintenance and aftercare of the turf. These must be specified separately. Advice can be obtained from Boddingtons Limited.*

### Summary of Test Methods

#### 1. Tensile strength

- Five samples are taken from the uncut net in both the longitudinal and traverse directions.
- Each sample to be five strands wide and long enough to allow a gauge length of 100mm.
- Cross-head speed 200mm/min
- The minimum tensile strength for any one sample shall be 165N with a minimum average for five samples of 170N.

#### 2. Junction strength

- Two perpendicular strands are cut from the net so that they are attached to each other by one junction.
- The two strands are bent and clamped so that their ends are at 180° to each other.
- With a cross head speed of 200mm/min the strands are pulled apart until the junction fails.
- The junction strength should be at least 50% of the average tensile strength for a strand, i.e. 17N.

#### 3. Flexural recovery

- Of a 100mm long Advanced Turf® element, 60mm of length are clamped adjacent to an edge having a radius of 3mm, so that 40mm projects out over this edge. (Discard the sample if the tip droops by more than 3° along the chord of the droop).
- Fold the samples 90° down over the edge, hold for five seconds, release, and after a further five seconds measure the angle to which it has reverted (along the chord).
- For 90% of samples, 90° minus the reverted angle should be at least 95% of 90° minus the original droop angle.

#### 4. Properties of mesh stabilised rootzone

These should be performed according to the USGA protocol. The acceptable ranges are not necessarily those of the USGA but will vary with application and should be discussed with Boddingtons Limited.

*Please note that the information above is given as a guide only. Boddingtons cannot be liable for damage caused by incorrect installation of this product. Final determination of the suitability of any information or material for the use contemplated and the manner of its use is the sole responsibility of the user and the user must assume all risk and responsibility in connection therewith.*

Copyright © Boddingtons Ltd. All rights reserved Advanced Turf® and Netlon® are registered trademarks of Conwed Plastics nv.



Certificate No. FM 33039

Blackwater Trading Estate • The Causeway • Maldon • Essex CM9 4GG • England  
**Tel: +44 (0) 1621 874200 Fax: +44 (0) 1621 874299**  
 e.mail: sales@boddingtons-ltd.com • www.grass-reinforcement.com

®  
Advancedturf

